

Material : Polyphenylene Sulfide with 40% Glass Filled

Spareage Code : PPS

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ASTM D 792, 23 °C	1.64-1.68	1.66	g/cm ³
Hardness ASTM D 785, 23 °C	M-100	M-100	Scale M
Tensile strength ASTM D 638, 23 °C	190Min	193	mpa
Elongation at break ASTM D 638, 23 °C	1.70Min	2.2	%
Heat Distortion ASTM D 648,Temp at 1.82mpa	---	270	°C